

51.106N | Total Glow Plus

Features

51.106N | Total Glow Plus is a photoluminescent, flexible polymeric vinyl with a matt finish, designed to be easily printable using a broad range of wide format printing methods including (eco)solvent, UV, and latex inks. The photoluminescent compounds within the film are capable of absorbing light, allowing the graphic to remain visible in blackout, dark or low light environments.

This versatile product is ideal for use in a range of indoor safety applications, including exit and fire safety signage in buildings, marine, rail and military applications (B-grade). With its high tack permanent adhesive, Total Glow Plus can be easily applied to a variety of substrates.

51.106N | Total Glow Plus (B-grade) is available in 1370mm (width) x 45,7m (length) rolls.

Total Glow series is also available in 51.107N | Total Glow Supreme (C-grade) and 51.105N | Total Glow (A-grade)

Technical & Performance Information

Film Thickness	190 micron
Adhesive Thickness	50 micron
Total Thickness	240 micron
Adhesive type	High tack permanent clear solvent-based acrylic
Release Liner	170 gsm double-sided PE coated kraft liner
Adhesion to steel (20 mins / 180°)	30 N/25mm
Adhesion to steel (24 hrs / 180°)	34 N/25mm
Luminous value* (after 10 mins)	110 mcd/m ²
Luminous value* (after 60 mins)	10 mcd/m ²
Dimensional Stability	Excellent
Application Temperature	+10 to +25 °C
Service Temperature	-30 to +65 °C
Opacity Level	Low
Printability	(eco)solvent, UV & latex

* Xenon lamp exposure - 1000Lx / 5 min (DIN 67510)

Warranty

iSee2 warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different.