



Solar Control and Energy Savings

Helios Spectrally Selective Exterior Film

XHE 70 ER HPR

Developmental Technical data [‡]	6mm clear single	6mm-12mm-6mm dual clear
Solar Energy Transmission, τ_e	33%	27%
Solar Energy Reflection, ρ_e	37%	39%
Solar Energy Absorption, α_e	30%	34%
Visible Light Transmission, τ_v	66%	59%
Visible Light Reflection (External), ρ_{ve}	9%	13%
Visible Light Reflection (Internal), ρ_{vi}	9%	15%
Ultraviolet Transmission, τ_{uv} (wavelengths 300-380nm)	<1%	
Solar Heat Gain Coefficient	0.42	0.34
Shading Coefficient	0.48	0.39
Total Solar Energy Rejected	58%	66%
Glare Reduction	25%	25%
Film Colour / Appearance	Light-Green	
Manufacturer's Limited Warranty	10 Years vertical / 5 Years sloping	

Installation Notes: Please follow Technical Bulletin 73 Installation, sealing and splicing guidelines and the NEW Technical Bulletin 85 Sealing with vinyl tapes.

Please check the complete Film to Glass Thermal Stress Compatibility Guidelines before film installation; Contact Eastman Performance Films for full details.

[‡]Based on data obtained during product development and subject to change. Data captured using National Fenestration Rating Council's (NFRC) guidelines on single nominal 6mm clear glass and dual nominal 6-12-6 mm clear glass. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.

Notice: Although the information and recommendations set forth herein (hereafter "Information") are presented in good faith and believed to be correct as of the date hereof, neither Eastman Chemical Company nor any of its subsidiaries or affiliates (collectively, "Eastman") makes any representations or warranties as to the completeness or accuracy thereof and assumes no obligation to update any of the Information. Information is supplied upon the condition that the persons receiving same will make their own determinations as to its suitability for their purposes prior to use. In no event will Eastman be held responsible for damages or liability of any nature whatsoever, including without limitation, for direct, indirect or consequential loss, business interruption, loss of profits, production, goodwill or contracts, or anticipated savings, resulting from the use of or reliance upon the Information or the product to which the Information refers. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose, or of any other nature are made hereunder with respect to information or the product to which information refers.

www.llumar.com

EASTMAN

©2020 Eastman Performance Films, LLC. Product brands referenced herein with a [™] or [®] symbol are trademarks of Eastman Chemical Company or its subsidiaries. All other trademarks are the property of their respective owners. Visual renderings are for illustrative purposes only; actual appearance may vary. All rights reserved. No liability is accepted for errors.