



21.000N | SlipStop 100

Total Mark | Lamination Films

Features

21.000N | SlipStop 100 is a clear matt textured polypropylene film suitable for indoor use. This product is developed as a short term (anti-slippery) overlamination for floor decals, roll-ups, table and counter top applications. Being a polypropylene, it is an economical and environmental friendly alternative to PVC films.

The SlipStop 100 offers a permanent acrylic adhesive, formulated to give exceptional clarity and bond strength. The adhesive will perform impeccably on most common printing inks. In case of specific ink formulations however, we advise to test before use.

In order to achieve a perfect end result, **we recommend to combine** the SlipStop 100 lamination film **with our 40.100N StrongTack or the 51.101N StrongTouch.**

Technical & Performance Information

Film Thickness	100 micron
Adhesive Thickness	25 micron
Total Thickness	125 micron
Adhesive Type	High Tack Permanent Clear Waterbased Acrylic
Release Liner	140 gsm liner
Artificial Weathering *	1 year
Adhesion to steel (20 mins / 180°)	14 N/25mm
Adhesion to steel (24 hrs / 180°)	22 N/25mm
Dimensional Stability	Excellent
Application Temperature	+ 5 to +25 °C
Service Temperature	- 40 to +95 °C

* equivalent to vertical exposure in Mid-European climate

Certifications

Anti-slip certification	R9
Indirect food contact	21CFR

Groendreef 35
B-9880 Aalter | Belgium
T +32 9 216 6700
F +32 9 216 6709
W www.isee2.eu

Warranty

iSee2 warrants our material for one (1) year from date of shipment. The shelf life of our material is dependent on storage conditions. We recommend that the end user stores the material in the original boxes (out of direct sunlight) from our factory. We also recommend to store our material at 21°C with 50% relative humidity. iSee2 only warrants our products to be free from defects in workmanship or defects in iSee2 material. We will replace or credit any material deemed defective. No acceptance or responsibility for loss, damage or expense implied or otherwise shall be assumed by the seller or manufacturer. User assumes all risk and liability in connection herewith. All data values quoted above are typical and should not be used to deem the product defective, if measured values are different