



30.905N | Spectra Flame

Transform any space with our dichroic window films, designed to infuse vibrant hues and mesmerizing iridescence. Try Spectra Flame for a stunning red shine.

FACE FILM

PET, gloss red-tinted dichroic

Thickness (µm)	100	
Tensile strength (N/mm ²)	200	EN ISO 527-3
Elongation at break (%)	137	EN ISO 527-3

ADHESIVE

Clear solvent-based acrylic, removable

Thickness (µm)	20	
Adhesion to steel		FINAT FTM 1
20 minutes (180°) N/25mm	3	
24 hours (180°) N/25mm	4	

RELEASE LINER

Clear PET liner

Thickness (µm)	50	
----------------	----	--

PRODUCT APPLICATION

Dimensional stability (.mm)	<1	FINAT FTM 14
Application temperature (°C)	10 to 25	
Service temperature (°C)	-30 to 60	

DURABILITY

Shelf Life (months)	18	
Outdoor durability (years)	1	Vertical exposure, Mid-EU climate

ROLL SIZES

1370mm x 50m

PRINTING METHOD

UV Tested on Mimaki UCJV 300-160

Fourbases BV guarantees the material for twelve months from the date of final invoice. The shelf life of our material depends on storage conditions. The end user should store the material in the original boxes or in equivalent boxes, away from direct sunlight, at a temperature of 21°C and 50% relative humidity. Fourbases BV guarantees that the products are free from defects in workmanship or defects in iSee2 material, provided they are stored properly. At its sole discretion, Fourbases BV may either: (1) replace all or part of the materials, or (2) issue a credit note for the value of the defective portion. All quoted data values are typical and should not be used as a basis to consider the product defective if measured values differ.

