

Technical Data Sheet

Issue date: 16/03/2009 Date last modification: 09/12/2016

## **GRAPHICS** - Wide Format Ink Jet Print Media

# 4-GL3C-04053 RI-JET 75 GLOSS CLEAR ASP26 PERMANENT WKPE144

### Face Material

Gloss clear polymeric vinyl.

Type Polymeric vinyl Colour and Finish Gloss clear

ISO-536 Weight 100 g/m<sup>2</sup> ±10% ISO 534-80 Thickness 75 µ ±10%

### Adhesive

Solvent based acrylic permanent adhesive featuring high cohesion and good water resistance. Designed for a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP).

ASP26 permanent Reference Type Acrylic permanent

+10°C Min. Appl. Temp.

Service Temp. -20°C/+130°C

Shear High

Medium N/inch<sup>2</sup> Tack Final Adhesion High N/inch

#### Liner

Siliconised two side PE Kraft Type

Colour and Finish White

PP-032 - ISO Weight 144 g/m<sup>2</sup>

536 ±10%

**Thickness** 155 u ±10% ISO 534 DIN 53 147-64 Transparency n.a. %

### **Applications**

For advertising and promotional applications (outdoor and indoor posters, billboards and signs) and for vehicle applications (flat sided including buses, trams and taxis).

### **Printing Methods**

The RI-JET series of ink-jet print media gives excellent print results with UV, solvent and eco-solvent ink-jet printing. Testing for suitability between media, printers and inks is always recommended prior to use.

### Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following STORAGE CONDITIONS:

- This material must be stored at a temperature of  $22^{\circ}C \pm 2^{\circ}C$  and  $50 \pm$ 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.





